


**Amendments to the Claims:**

The following listing of claims replaces all other versions of claims previously presented.

**Listing of Claims:**

1 (Currently Amended): A rare earth magnet, comprising:

a sintered body including: rare earth magnet particles; and a rare earth oxide being present between the rare earth magnet particles, the rare earth oxide being represented by a following general formula ( I ):



where R is any one of terbium, dysprosium, holmium, erbium, thulium, ytterbium, and lutetium,

wherein the rare earth magnet particle is constituted by a cluster of numerous crystal grains, and

an electric resistivity of the rare earth magnet is 26.0  $\mu\Omega\text{m}$  or more.

2 (Canceled)

3 (Original): The rare earth magnet of claim 1,

wherein the rare earth magnet is a Nd-Fe-B type magnet.

4 (Original): The rare earth magnet of claim 1,

wherein the rare earth magnet is an anisotropic magnet.

5 (Currently Amended): A method of manufacturing a rare earth magnet, comprising:

forming a rare earth magnet particle constituted by a cluster of numerous crystal grains,

preparing a mixture including the rare earth magnet particle and a rare earth oxide being represented by a following general formula ( I );



where R is any one of terbium, dysprosium, holmium, erbium, thulium, ytterbium, and lutetium;

filling the mixture in a molding die; and

molding the mixture at a temperature of 600°C to 850°C.

6 (Previously Presented): The method of manufacturing a rare earth magnet of claim 5, further comprising:

between the filling and the molding, pre-molding the mixture while the rare earth magnet powder being subjected to magnetic field orientation,

wherein the rare earth magnet particle is anisotropic magnet.

7 (Previously Presented): The method of manufacturing a rare earth magnet of claim 5, wherein the molding is a step which molds the mixture by pressure sintering.

8 (Currently Amended): A motor, comprising:

a rare earth magnet including a sintered body having rare earth magnet particles and a rare earth oxide being present between the rare earth magnet particles, the rare earth oxide being represented by a following general formula ( I ):



where R is any one of terbium, dysprosium, holmium, erbium, thulium, ytterbium, and lutetium,

wherein the rare earth magnet particle is constituted by a cluster of numerous crystal grains, and

an electric resistivity of the rare earth magnet is 26.0  $\mu\Omega\text{m}$  or more.

9 (Currently Amended): The rare earth magnet of claim 1,  
wherein a size of the rare earth magnet particle is in a range from ~~[[1]]~~ 10  $\mu\text{m}$  to 500  $\mu\text{m}$   
inclusive, and a size of the crystal grain is 500 nm or below.

10 (Previously Presented): The rare earth magnet of claim 1,  
wherein a size of the crystal grain is not greater than a single-domain critical grain size.

11 (Previously Presented): The rare earth magnet of claim 1, further comprising:  
a protective film provided on a surface of the rare earth magnet.

12 (Previously Presented): The method of manufacturing a rare earth magnet of claim 5,  
wherein the rare earth magnet particle is formed by HDDR method or UPSET method.

13 (Canceled)

14 (Currently Amended): The method of manufacturing a rare earth magnet of claim 5,  
wherein a size of the rare earth magnet particle is in a range from ~~[[1]]~~ 10  $\mu\text{m}$  to 500  $\mu\text{m}$   
inclusive, and a size of the crystal grain is 500 nm or below.

15 (Previously Presented): The method of manufacturing a rare earth magnet of claim 5,  
wherein the preparing the mixture is performed by MOCVD method.

16 (Currently Amended): The motor of claim 8,  
wherein a size of the rare earth magnet particle is in a range from ~~[[1]]~~ 10  $\mu\text{m}$  to 500  $\mu\text{m}$   
inclusive, and a size of the crystal grain is 500 nm or below.

17 (Previously Presented): The motor of claim 8,  
wherein a size of the crystal grain is not greater than a single-domain critical grain size.

18 (Previously Presented): The motor of claim 8,  
wherein the rare earth magnet is coated with a protective film.

19 (New): The rare earth magnet of claim 1,

wherein a content of the rare earth oxide in the rare earth magnet is within a range from 0.1 mass% to 20 mass%.

20 (New): The rare earth magnet of claim 19,

wherein the content is within a range from 1 mass% to 5 mass%.

21 (New): A rare earth magnet, comprising:

a sintered body including: rare earth magnet particles; and a rare earth oxide being present only between the rare earth magnet particles, the rare earth oxide being represented by a following general formula ( I):



where R is any one of terbium, dysprosium, holmium, erbium, thulium, ytterbium, and lutetium,

wherein the rare earth magnet particle is constituted by a cluster of numerous crystal grains.

22 (New): The rare earth magnet of claim 21,

wherein the rare earth magnet is a Nd-Fe-B type magnet.

23 (New): The rare earth magnet of claim 21,

wherein the rare earth magnet is an anisotropic magnet.

24 (New): The rare earth magnet of claim 21,

wherein a size of the rare earth magnet particle is in a range from 10  $\mu\text{m}$  to 500  $\mu\text{m}$  inclusive, and a size of the crystal grain is 500 nm or below.

25 (New): The rare earth magnet of claim 21,

wherein a size of the crystal grain is not greater than a single-domain critical grain size.

26 (New): The rare earth magnet of claim 21, further comprising: a protective film provided on a surface of the rare earth magnet.

27 (New): The rare earth magnet of claim 21,  
wherein an electric resistivity of the rare earth magnet is  $26.0 \mu\Omega\text{m}$  or more.

28 (New): The rare earth magnet of claim 21,  
wherein a content of the rare earth oxide in the rare earth magnet is within a range from 0.1 mass% to 20 mass%.

29 (New): The rare earth magnet of claim 28,  
wherein the content is within a range from 1 mass% to 5 mass%.

30 (New): A motor, comprising:  
a rare earth magnet including a sintered body having rare earth magnet particles and a rare earth oxide being present only between the rare earth magnet particles, the rare earth oxide being represented by a following general formula ( I ):



where R is any one of terbium, dysprosium, holmium, erbium, thulium, ytterbium, and lutetium,

wherein the rare earth magnet particle is constituted by a cluster of numerous crystal grains.

31 (New): The motor of claim 30,  
wherein a size of the rare earth magnet particle is in a range from  $10 \mu\text{m}$  to  $500 \mu\text{m}$  inclusive, and a size of the crystal grain is  $500 \text{ nm}$  or below.

32 (New): The motor of claim 30,  
wherein a size of the crystal grain is not greater than a single-domain critical grain size.

**Application No.: 10/600,602**

33 (New): The motor of claim 30,

wherein the rare earth magnet is coated with a protective film.

34 (New): The motor of claim 30,

wherein an electric resistivity of the rare earth magnet is  $26.0 \mu\Omega\text{m}$  or more.